

č.	Názov	Zloženie									
		Au	Ag	Cu	Zn	Ni	Pd	Cd	Pt	In	iné
1	Zlato žlté 320	585	320	95	0	0	0	0	0	0	0
2	Au f. 320	585	320	95	0	0	0	0	0	0	0
3	Au f. 140	585	140	275	0	0	0	0	0	0	0
4	Au f. 50	585	50	365	0	0	0	0	0	0	0
5	Spájka M	585	150 - 160	120 - 130	5	0	0	125 - 135	0	0	0
6	Au Biele super	585	250	0	0	0	165	0	0	0	0
7	Zlato poločervené 140	585	140	275	0	0	0	0	0	0	0
8	Zlato červené 50	585	50	365	0	0	0	0	0	0	0
9	Spájka žltá, mäkká	585	155	125	5	0	0	130	0	0	0
10	Zlato biele super 25	585	250	0	0	0	165	0	0	0	0
11	Zlato 750/000	750	150	100	0	0	0	0	0	0	0
12	Striebro 925/000	0	925	75	0	0	0	0	0	0	0
13	Zlato tmavožlté 280	585	280	135	0	0	0	0	0	0	0
14	Zlato biele tvrdé	585	0	250	50	115	0	0	0	0	0
15	Zlato žltozelené 380	585	380	35	0	0	0	0	0	0	0
16	Zlato dentál 650 K	650	305	0	0	0	30	0	15	0	0
17	Zlato biele BT	585	0	250	50	115	0	0	0	0	0
18	Spájka T	585	165	150	5	0	0	95	0	0	0
19	Zlato f. 380	585	380	35	0	0	0	0	0	0	0
20	Striebro 925	0	925	75	0	0	0	0	0	0	0
21	Striebro 925	0	925	75	0	0	0	0	0	0	0
22	Striebro 999	0	999	0	0	0	0	0	0	0	0
23	Striebro 750	0	750	250	0	0	0	0	0	0	0
24	Zlato 750 červené	750	50	200	0	0	0	0	0	0	0
25	Zlato 750 biele Pd	750	100	0	0	0	150	0	0	0	0
26	Zlato 750 biele Ni	750	0	50	50	150	0	0	0	0	0
27	Zlato 986	986	0	14	0	0	0	0	0	0	0
28	Zlato 585 biele špeciál U	585	0	283	47	85	0	0	0	0	0
29	Zlato 585 spájka stredná bez Cd	585	135	150	96	0	0	0	0	34	0

	Pokračovanie	Au	Ag	Cu	Zn	Ni	Pd	Cd	Pt	In	iné
30	Au 14 biele Ideál	585	0	283	48	83	0	0	0	0	0
31	Zlato 750 biele špeciál UNI	750	0	165	30	55	0	0	0	0	0
32	Au 750 BTU	750	5	145	50	50	0	0	0	0	0
33	750/1000 Au-žltá	750	125	125	0	0	0	0	0	0	0
34	750/1000 Au-červená	750	68	182	0	0	0	0	0	0	0
35	Au 585 BTU	585	8	241	83	83	0	0	0	0	0
36	Pt 950	0	0	50	0	0	0	0	950	0	0
37	Au Bledožlté 585/320	585	320	95	0	0	0	0	0	0	0
38	Au Ružové 585/140	585	140	275	0	0	0	0	0	0	0
39	Au Červené 585/50	585	50	365	0	0	0	0	0	0	0
40	Au Spájka 585 žltá	585	58	234	97	0	0	26	0	0	0
41	Au Žlté 585/280	585	280	135	0	0	0	0	0	0	0
42	Au Žlté 750/150	750	150	100	0	0	0	0	0	0	0
43	Ag 925	0	925	75	0	0	0	0	0	0	0
44	Ag spájka stredná	0	600	275	125	0	0	0	0	0	0
45	Biele 585 Ni-P	585	0	295	60	55	0	0	0	0	0
46	Ag 925 AX 1	0	925	74	0	0	0	0	0	0	1
47	Ag 925 AX 2	0	925	74	0	0	0	0	0	0	1
48	Au Žlté 585/280	585	280	135	0	0	0	0	0	0	0
49	Au Ružové 585/140	585	140	275	0	0	0	0	0	0	0
50	Au Červené 585/50	585	50	365	0	0	0	0	0	0	0
51	Au BIELE 585/WA	585	8,3	240,7	83	83	0	0	0	0	0
52	Au Spájka žltá 585	585	124,5	137	103,7	0	0	0	0	0	49,8
53	Au Spájka biela 585	585	99,6	145,3	95,4	41,5	0	0	0	0	33,2
54	Au Bledo žlté 585/320	585	320	95	0	0	0	0	0	0	0
55	Au Spájka biela mäkká TB 14	585	41,5	195	107,9	70,6	0	0	0	0	0
56	Au Spájka biela stredná MB 14	585	0	224,1	45,7	107,9	0	0	0	37,3	0
57	Au Spájka žltá mäkká TG 14	585	141,1	161,8	37,4	0	0	0	0	74,7	0
58	Au Spájka žltá stredná MG 14	585	157,7	166	41,5	0	0	0	0	49,8	0
59	Au Spájka červená stredná	585	80	215	0	0	0	120	0	0	0
60	Au 18 k biele T50/0	750	0	162,5	35	52,5	0	0	0	0	0
61	Au 14k biele paládiové	585	255	0	0	0	160	0	0	0	0

	Pokračovanie	Au	Ag	Cu	Zn	Ni	Pd	Cd	Pt	In	iné
62	Au 18k biele paládiové	750	50	0	0	0	200	0	0	0	0
63	Au 14k žltá 2NL	585	278	124,5	12,5	0	0	0	0	0	0
64	Spájka Ag 600 extra - flow	0	600	275	60	0	0	65	0	0	0
65	Ag 925 1 Pag/M	0	925	73,5	1,5	0	0	0	0	0	0
67	Au 585 "BIELE EXTRA"	585	60	220	70	65	0	0	0	0	0
68	Au 585 " PINK" /ružové/	585	60	345	10	0	0	0	0	0	0
69	Au 585 "RED" /červené/	585	10	400	5	0	0	0	0	0	0
70	Au 585 " BIELE EXTRA I"	585	0	285	68	62	0	0	0	0	0
71	14K biele T50	585	0	257	53	103	0	0	0	0	áá3
72	14k žltý špeciál	585	310	95	10	0	0	0	0	0	0
73	925 CuZn	0	925	69	6	0	0	0	0	0	0
74	STRIEBRO 925	0	928	72	0	0	0	0	0	0	0
75	Ag 925 ORIG	0	935	64	0	0	0	0	0	0	1
76	LGY	585	66,4	282,2	66,4	0	0	0	0	0	0
77	MN19	585	0	257,3	74,7	83	0	0	0	0	0
78	ID03	585	261,7	142,3	10,9	0	0	0	0	0	0
80	14 kt biele zlato s paládiom	585	262	45	4	0	104	0	0	0	0
81	14 kt biele zlato X1 TM	585,5	0	175	89,5	150	0	0	0	0	0
82	18 kt jemné biele zlato	757	0	131	50	62	0	0	0	0	0
83	18 kt červené zlato	753	12	233	2	0	0	0	0	0	0
84	18 kt žlté zlato Royal	753	165	67	15	0	0	0	0	0	0
85	Platina s Kobaltom.950	0	0	0	0	0	0	0	950	50	0
79	Platina s Ruténium.950	0	0	0	0	0	0	0	950	0	50 Ru
86	Striebro s Paládiom	0	925	30	10	0	35	0	0	0	0
87	18 kt biele zlato s paládiom	750	0	83	0	0	167	0	0	0	0
88	14 kt štandardné žlté zlato -euro	585	115	225	75	0	0	0	0	0	0
89	14 kt biele zlato na čisté odlievanie	585	0	215	90	110	0	0	0	0	0
90	Biela J "585"	585	0	265	70	80	0	0	0	0	0
91	Červená J "585"	585	15	385	15	0	0	0	0	0	0
92	Žltá J "585"	585	85	275	55	0	0	0	0	0	0
93	585GG15	585	305	100	10	0	0	0	0	0	0
94	Pd tvrdá	585	60	145	10	0	200	0	0	0	0

	Pokračovanie	Au	Ag	Cu	Zn	Ni	Pd	Cd	Pt	In	iné
95	ELA 2	585	60	265	45	40	0	0	0	0	5 "In"
96	0002 FINE SILVER	0	999,5	0	0	0	0	0	0	0	0,5
97	Au ružové	587	15	388	10	0	0	0	0	0	0
98	Au biele	587	10	310	60	33	0	0	0	0	0
99	Au žlté	587	318	90	5	0	0	0	0	0	0
100	Spájka -Au 585 žltá -stredná LSGS	585	164	85	153,5	0	0	0	0	0	12,5 In
101	Spájka - Au 585 žltá - tvrdá LSGT	585	133	145	95	0	0	0	0	0	42 In
102	Spájka 585 P/R	585	20	309	11	0	0	0	0	0	75 In
103	L-W-585	585	0	290,5	70,55	53,95	0	0	0	0	0
104	L-W-375	375	0	437,5	106,25	81,25	0	0	0	0	0
105	L-W-750	750	0	175	42,5	32,5	0	0	0	0	0
106	L-Y-375	375	150	381,25	93,75	0	0	0	0	0	0
107	L-Y-585	585	99,6	253,15	62,25	0	0	0	0	0	0
108	L-Y-750	750	60	152,5	37,5	0	0	0	0	0	0
109	P-R-375	375	25	581,25	18,75	0	0	0	0	0	0
110	P-R-585	585	16,6	385,95	12,45	0	0	0	0	0	0
111	P-R-750	750	10	232,5	7,5	0	0	0	0	0	0
112	Ag 925 DreamT	0	925	54	21	0	0	0	0	0	0
113	Au 585 biele INTERESANT	585	0	232	63	120	0	0	0	0	0
114	Au 14.kar.268	585	268	147	0	0	0	0	0	0	0